

Enviro-Syn<sup>®</sup> HCR-3000<sup>®</sup> a Dorf Ketal Technology, is a strong environmentally-friendly Synthetic Acid<sup>™</sup> solution, designed to reduce the risks associated with exposure, corrosion, and negative HSE properties commonly linked to HCl.

### APPLICATIONS

- ✓ Formation stimulation, scale removal and workover treatments
- ✓ High temperature
  - SAGD
  - CSS
  - Geothermal
- ✓ Ideal for applications where a strong acid is required and high temperatures or exotic metals are exposed
  - Chrome/chrome plating-plated
  - Aluminium
  - Copper
  - Brass

### FEATURES & BENEFITS

- ✓ Chloride free
- ✓ Comparable solubilizing capabilities to 20% HCl
- ✓ Minimal reprecipitation at high pH levels (> 4)
- ✓ Blends available up to 180°C (356°F)\*
- ✓ Compatible with typical oilfield elastomers (e.g., Viton, Nitrile and EPDM)
- ✓ Stable corrosion inhibitor (CI) package, free of hazardous chemicals such as formic acid and propargyl alcohol (PA)
- ✓ Non-regulated for transportation

\*Temperature limitations may vary based on specific well conditions



### PHYSICAL PROPERTIES

Specific Gravity:	1.2
Freezing Point:	≈ -30°C (-22°F)
Boiling Point:	> 100°C (212°F)
pH:	< 1.0
Solubility:	Soluble in water

### SUPPORT HSE AND ESG GOALS



Non-corrosive  
to skin



Non-fuming



Biodegradable



Non-regulated for  
air, land and sea  
transport

## TOTAL SOLUBILITY

Table 1. Total solubility of Enviro-Syn HCR-3000 on a variety of scales.

Acid	Scale	Total Solubility (kg/m <sup>3</sup> )	Total Solubility (lb/gal)
20% HCl	CaCO <sub>3</sub>	253	2.1
HCR-3000 Concentrate	CaCO <sub>3</sub>	280	2.3
HCR-3000 Concentrate	CaMg(CO <sub>3</sub> ) <sub>2</sub>	190	1.6
HCR-3000 Concentrate	FeS	170	1.42

NOTE: High temperature corrosion inhibitor loadings can alter total solubilizing ability.

## CORROSION RATES

With ultra-low metal corrosion properties, Enviro-Syn HCR-3000 has corrosion rates that are well below oilfield industry accepted values on typical oilfield alloys.

Table 2. Corrosion rates of Enviro-Syn HCR-3000 blends on oilfield alloys.

Blend (HCR:water)	Temp (°C / °F)	Coupon	Time (hr)	Corrosion (mm/yr)	Corrosion (lb/ft <sup>2</sup> )
Concentrate	90 / 195	N-80	6	0.584	0.001
Concentrate	90 / 195	QT-800	6	0.851	0.001
1:1	130 / 256	N-80	6	2.464	0.003
Concentrate	130 / 256	QT-800	6	12.392	0.014
1:1	90 / 195	N-80	6	2.692	0.003
1:1	90 / 195	QT-800	6	4.772	0.005
1:1	130 / 256	N-80	6	5.577	0.006
1:1	180 / 355	J-55	4	11.939	0.003
1:1	160 / 320	QT-900	3	28.321	0.019
1:1	150 / 302	L80	4	9.724	0.007

NOTE: Oilfield industry typically accepts a corrosion rate less than 0.050 lb/ft<sup>2</sup> at 6 hours. Coiled tubing typically accepts a corrosion rate less than 0.020 lb/ft<sup>2</sup> at 6 hours.

Table 3. Corrosion rates of Enviro-Syn HCR-3000 blends on chrome alloys.

Blend (HCR:water)	Temp (°C / °F)	Coupon	Time (hr)	Corrosion (mm/yr)	Corrosion (lb/ft <sup>2</sup> )
Concentrate	60 / 140	Chrome plated 1018CS	6	0.360	0.000
Concentrate	90 / 195	Chrome plated 1018CS	6	0.291	0.000
1:1	110 / 230	Super Duplex 2507	6	0.0038	0.000
1:1	110 / 230	Duplex 2205	6	1.022	0.001
1:1	200 / 392	Duplex 2205	3	24.821	0.014

All corrosion testing was completed with fresh water.  
 Corrosion testing recommended with dilution water prior to treatment.



# Fluid<sup>®</sup>

A CORP KETAL COMPANY

PRODUCT DATA SHEET

## Enviro-Syn<sup>®</sup> HCR-3000<sup>®</sup>

Chloride Free, Chrome Safe Synthetic Acid™ System

### SAFETY, STORAGE & HANDLING

- ✓ Store in sealed containers, such as plastic pails, lined drums and HDPE IBC totes
- ✓ Fittings and valves should be HDPE, brass or stainless steel
- ✓ Store out of direct sunlight
- ✓ Consult SDS for additional information and PPE requirements
- ✓ Shelf life of > 1 year; confirm corrosion if product sits for > 60 days

**Talk to us today about our revolutionary products available globally.**

[info@fluidenergyltd.com](mailto:info@fluidenergyltd.com) or [www.fluidenergyltd.com](http://www.fluidenergyltd.com)

The Fluid logo, Enviro-Syn, HCR-3000 and Synthetic Acid are trademarks or registered trademarks of Fluid Energy Ltd., in Canada and other countries. To the best of our knowledge, the information contained herein is accurate and reliable; however, we provide no guarantees or warranties, express or implied, and we do not assume any liability for the accuracy or completeness of such information, as conditions and methods for use are beyond our control. Some or all of the products or methods discussed herein may be covered by one or more patents or patents pending. No freedom from infringement of any patent owned by us or others is to be inferred. © 2024, Fluid Energy Ltd. 8-JAN-2026